THERMORY®

PROFILE CAR3

0

Radiata pine, also known as clear pine, is a knot-free pinewood.

0

Thermal modification enhances radiata pine's smooth, elegant look by giving it a warm caramel-brown color.

Each and every board is unique, with the individual natural grains coming together to create a beautiful pattern.

Thermal modification improves radiata pine's dimensional stability and makes the wood more durable.

Data sheet

Thermally modified radiata pine cladding

An elegant, knot-free look in durable softwood.

0

To further protect the durability of the cladding boards, we recommend treating them on all four sides with oil or paint prior to installation.

With its low moisture absorption, thermally modified radiata pine twists, cups and bends less than untreated wood in outdoor use, with less shrinkage and expansion.

0

Thermory's thermo-radiata pine is chemical free, with no harmful waste generated.

C34



IM

END JOINT:

FIXING:

Hidden/visible

d joint:

Optional (in 42 mm thickness not available)

Intense 220 °C
3.0 - 5.7 m; lengths are subject to availability
Radiata pine (<i>Pinus radiata</i>)
44091018





Data sheet

CHARACTERISTICS OF THERMALLY MODIFIED RADIATA PINE (SAWN, PLANED AND PROFILED):			CORRESPONDING STANDARD/TEST REPORT
DURABILITY CLASS (CATAS)		Variable 1 to 3: very durable to moderately durable	EN 350:2016
USE CLASS		3.1 – exterior, above ground, exposed to the weather. Limited wetting condtions.	EN 335:2013
REACTION TO FIRE CLASSIFICATION (CLADDING ONLY): - thickness: ≥18 mm - min thickness within profile: 9 mm - valid for profiled claddings and straight edged boards without air gap - without surface coating		D-s2, d0	EN 13501-1:2018
INITIAL MOISTURE CONTENT (%)*		11.3 ± 2	Internal factory test 01.10.2022
OVEN-DRY DENSITY (KG/M³)*		414.9 ± 9.2	ISO 13061-2:2014
EQUILIBRIUM MOISTURE CONTENT AT 21°C, (%)* AT:	RH 35%	4.4 ± 0.3	ISO 13061-1:2014
	RH 60%	7.5 ± 0.2	
	RH 90%	12.5 ± 0.1	
SWELLING FROM OVEN-DRY DIMENSIONS IN RADIAL FIBRE DIRECTION AT 21 °C (%)* AT:	RH 35%	0.6 ± 0.1	ISO 13061-15:2017
	RH 60%	0.8 ± 0.1	
	RH 90%	1.3 ± 0.1	
SWELLING FROM OVEN-DRY DIMENSIONS IN TANGENTIAL FIBRE DIRECTION AT 21 °C (%)* AT:	RH 35%	1.3 ± 0.1	
	RH 60%	1.7 ± 0.1	
	RH 90%	2.4 ± 0.1	
BENDING STRENGTH (N/MM ²)*		40 ± 4.6	EN 408:2010
MODULUS OF ELASTICITY (N/MM ²)*		10377 ± 703.7	EN 408:2010
COMPRESSIVE STRENGTH (N/M	M²)*	50.8 ± 2.6	EN 408:2010
SCREW TRACTION RESISTANCE	(N/MM²)	18.3 ± 0.8	EN 1382:2016
JANKA HARDNESS (N)*		1763 ± 119.7	ISO 13061-12:2017
BRINELL HARDNESS (N/MM ²)*		15.39	EN 1534:2010
SCRATCH RESISTANCE (N)*		0.2	EN 15186:2012
ACIDITY (PH)*		3.74	ISO 6588-2:2021

*The values given are the mean results of testing, apply only in the aforementioned conditions and are not partially applicable.



Data sheet

COLOR	Golden Brown with a slight bronze glow (Colour variations in thermally modified wood are	
	a result of variations in growth conditions of the tree and are fully acceptable. Wood will weather to grey unless an UV resistant coating is applied and maintained.		
COATING	Many colour options available. Please contact our sales team for further information.		
GRADING	Grades "Clear" and "Country"	Grading rules, installation and maintenance manuals are at:	
SURFACE	Planed and brushed surface possible on Thermory Radiata Pine Cladding.		
EPD (RTS)	THERMALLY MODIFIED SOFTWOOD WITHOUT SURFACE COATING	GWP – BIOGENIC A1-A3: -7.83E1 kg CO2e per 1 m³	
	THERMALLY MODIFIED SOFTWOOD WITH SURFACE COATING	GWP – BIOGENIC A1-A3: -7.71E1 kg CO₂e per 1 m³	
GENERAL INFO:			
COUNTRY OF ORIGIN	Estonia		
HANDLING	Thermory [®] cladding boards should be stored inside, out of the sun, rain and other elements. When this is not possible, boards need to be elevated off the ground, stacked uniformly and covered with a waterproof tarp. Leave the ends of the tarp open so moisture is not trapped inside, making certain the stored wood is not subjected to the elements or sun as UV rays will fade the material. Under no circumstances should Thermory [®] boards, even in original packaging, be subjected to rain or any moisture as they cannot dry properly when stacked and/or packaged.		
	sun as UV rays will fade the material. Unde even in original packaging, be subjected t properly when stacked and/or packaged.	er no circumstances should Thermory® boards, to rain or any moisture as they cannot dry	
WASTE MANAGEMENT	s not trapped inside, making certain the s sun as UV rays will fade the material. Under even in original packaging, be subjected t properly when stacked and/or packaged. Thermory naturally enhances wood using does not need to be treated as hazardou	only heat and steam. Thermally modified wood s waste.	
WASTE MANAGEMENT CHAIN OF CUSTODY CERTIFICATION	Thermory naturally enhances wood using does not need to be treated as hazardou FSC® and PEFC® certified products availal profiles and dimensions.	only heat and steam. Thermally modified wood s waste.	
WASTE MANAGEMENT CHAIN OF CUSTODY CERTIFICATION MANAGEMENT SYSTEM CERTIFICATIONS	Thermory naturally entanties wood using does not need to be treated as hazardou.	only heat and steam. Thermally modified wood s waste.	

THERMORY® Radiata Pine is produced at 220 °C in a special computer-controlled kiln. The process uses only heat and steam, no chemicals are added.

During the modification process, chemical and structural changes occur within the timber which improve some of its basic characteristics. The resulting product is more durable and stable – an ideal material for use in exposed areas such as external facades.

THERMORY_®

Data sheet



Leave a lasting impact

THERMORY is a world leader in the thermal modification of wood. We offer high-quality, long-lasting solutions that benefit from environmentally friendly technology. We have spent the past two decades developing our expertise through close collaboration with architects, designers, builders and homeowners – constantly revising our product selection and refining our technology in the process.

THERMORY promotes a transparent and responsible corporate culture. We care about the environment and treat nature with deep respect. Our purchasing process is environmentally responsible, and we exercise high standards for quality and sustainability. Our timber is carefully inspected and harvested from sustainably managed forests. If desired, we can offer PEFC, FSC® or Nordic Swan Ecolabel-certified wood.



As a renewable resource that is both durable and an excellent insulator, wood is one of the most environmentally friendly choices for your construction pro-



Last updated: May 2024. All previous vearsions are null and void. jects. If you think it's important to protect our valuable resources long into the future, then we're on the same mission. We create lasting value, because we want to leave behind a more harmonious and sustainable world.

REAL WOOD PRODUCTS WITH BEAUTY AND STABILITY IN EVERY FIBER

- O DECKING
- CLADDING
- INTERIOR
- SAUNA

in Thermory AS



Thermory's project 'Development of Resource-efficient Painted Thermally-modified Wood' is financed in cooperation with Enterprise Estonia (EAS) and the Norwegian Green ICT financing mechanism.



ightarrow thermory.com